


Declaration of Performance

CDECK Hollow and Solid Board

Characteristics	Unit.	Based on	Declared values and classes ¹	
			Hollow Profile	Solid Profile
Dimensions - Thickness	mm	EN 15534	24	
Dimensions - Width			140	
Swelling thickness	%	EN 317	0,4	0,3
Water absorption			1,1	0,6
Bending strength	N/mm ²	EN 310	48	57
Modulus of elasticity in bending (distance between supports 500mm)			6600	5500
Bending strength (characteristic value)	N/mm ²	EN789	40	46
Modulus of elasticity in bending (distance between supports 1080mm)			7300	7000
Impact strength (+23°C/1kg)	-	EN 477	80 cm (7,8 J) (No rupture)	200 cm (19,6J) (No rupture)
Impact strength (-10°C/1Kg)			100 cm (9,8J) (No rupture)	200 cm (19,6J) (No rupture)
Point load capacity (characteristic value)	N	EN 1533	6810	8780
Mechanical fastener holding capacity (characteristic value)	N	-	1330 N (Clip Quick-Fix Intermédio) 1040 N (Clip Quick-Fix Pró Intermédio)	
UV radiation resistance (1000H)	kJ/m ²	EN ISO4892-2	Before ageing: 3,95	
Charpy impact strength		EN ISO179-1	After ageing: 4,99	
Thermal expansion coefficient (-40°C, 80°C)	-	ASTM E228 EN821-1	(21,3 ± 0,1) x 10 ⁻⁶ K ⁻¹ (x direction) (50,6 ± 0,8) x 10 ⁻⁶ K ⁻¹ (y direction)	
Density	g/cm ³	EN ISO 1183-1	1,392	
Influence of moisture (surface hardness)	N/mm ²	EN 317 EN15534	94	101
Reaction to fire	-	ASTM E84-2017	20 (Class A)	15 (Class A)
		EN13501-1 EN ISO9239-1 ISO11925-2	B fl - s1	
Slipperiness	-	EN15534	Ok - Class 3	

¹ IHT assumes a variation of 30% due to the process production and to factors climatic exposure.

Soûre, July 5, 2023



Marco Duarte
General Manager